



# Gold Leaf Italian




PDF file for comparative use only.

# Best

**Best** gold leaf average thickness is 0.36 to 0.5 microns.



Fine Gold  
IT24.00FG AW=24g  
100% GOLD



Swiss Restorer 23 3/4 kt  
IT23.75SR AW=22g  
99% GOLD



Glass 23 kt  
IT23.00GL AW=18g  
96.5% GOLD




Surface 23 kt ◆  
IT23.00SF AW=18g  
98.5% GOLD



Red 23 kt  
IT23.00RG AW=18g  
96% GOLD



Glass 22 kt  
IT22.00GL AW=16g  
92% GOLD



Surface 22 kt ◆  
IT22.00SF AW=16g  
92% GOLD



White 12 kt ◆  
IT12.00WH AW=22g  
50% GOLD



Silver ◆ & Silver 5"x5"  
IT00.00SV AW=29g  
IT130SV AW=50g  
100% SILVER

Loose leaf oil gilded on white paper. The ◆ indicates leaf that is also available in patent form.

AW = Average total weight (gold + alloy) indicated in grams per 1000 leaves.

The ■ indicates leaf that is available as Ribbon Gold Leaf.